



COLOURED GROUT

Characteristics:

- RLA / Atlas Coloured Grout is a cement based grout it is designed for use with most types of Ceramic, Mosaic and Natural Stone tiles.
- It can be used on internal & external wall and floor surfaces. It can be used in grout joints from 1-5mm wide (Smooth White Grout 1-3mm).
- RLA / Atlas Coloured Grout contains a biocide therefore making it mould resistant.
- RLA / Atlas Coloured Grout can be applied in wet areas and areas of water immersion, like swimming pools, spas etc, with the use of Uniflex additive.

Preparation:

- Ensure that the adhesive has had sufficient time to cure prior to commencing grouting. This is generally 24 hours at 20°C.
- Remove spacer lugs out from the joint and rake out any adhesive that may have oozed out of the joint.
- Clean the joint from any dust or loose particles. Then dampen the joint prior to commencing grouting. NOTE: Do not flood the joint.

Mixing:

- The mixing ratio of Smooth White Grout is 5L of water per 15kg bag. The mixing ratio of other colours is 3 to 3.5L of water for a 15kg bag.
- Pour clean water into a pail and then gradually add the grout while mixing continuously until a smooth lump free mix is obtained. Always add powder to liquid.
- Allow the mix to stand for 10 minutes, re-stir and then apply the grout onto the tiles.
- When grouting in areas where movement is anticipated (or when grouting in swimming pools). Use 1 part Uniflex with 2 parts water.

Application:

- Use a rubber float to apply the grout onto the tiled surface. Apply the grout into the joints using a diagonal motion, ensuring that the grout goes into the entire depth of the joint and does not just bridge the joint.
- Remove the excess grout from the surface of the tiles with the rubber float ensuring that you do not dislodge the grout in the joint.
- Then use a damp sponge to clean the remainder of the grout off the tile surface. Regularly rinse the sponge and squeeze dry, to assist the cleaning.
- Allow the grout to cure for at least 24 hours at 20°C prior to commencing the final clean up. This time use a soft cloth to remove the haze.

Clean Up:

- Excess grout can be cleaned off tools etc. using water while the grout is still wet.

Coverage:

- The coverage of Coloured Grout will depend upon the size and thickness of the tile and the width of the grout joint. See over for coverage guide.

Packaging/Shelf Life:

- Coloured Grout is available in 15kg, 5kg & 2kg bags.
- A bag of Coloured Grout, when stored in a cool, dry environment, and is stored above ground level, will have a shelf life of approximately 12 months.

FEATURES

Polymer Modified
Mould Resistant
Internal/External
Wall/Floors
Range of colours



Handy tips:

- Do not apply Coloured Grout in temperatures above 40°C and below 5°C.
- Do not apply Coloured Grout in expansion joints use a flexible silicone sealant for that.
- Do not use strong acids to clean Coloured Grout.
- For applications/situations not mentioned in these instructions please contact your nearest RLA office.
- Coloured Grout is classified as a hazardous product.
- Coloured Grout being cement based is alkaline in nature and therefore may cause dermatitis. It is recommended that applicators wear PVC gloves or similar and safety gloves.
- For a full MSDS on this product please contact your nearest RLA office or Atlas office.

Coverage:

- The coverage of Coloured Grout will depend upon the size and thickness of the tile and the width of the grout joint. As a general guide:

Tile Size mm	Qty Grout required kg/m ² Joint width 1.5mm	Qty Grout required kg/m ² Joint width 3mm
50X50x6	0.8	1.6
150X150x6	0.3	0.6
200X100x6	0.3	0.6
200X200x6	0.2	0.4
300x300x6	0.13	0.26
400X400x10	0.17	0.34
600X600x10	0.11	0.20

Disclaimer: The information supplied is to the best of our knowledge true and accurate. The actual application of the product is beyond the manufacturers control. Any failure or damage caused by the incorrect usage of the product is not the responsibility of the manufacturer. The manufacturer insists that all workmanship must be carried out in accordance with AS 3958.1-2007. It is also the responsibility of the end user to ensure that the literature in their possession is the latest issue.

Technical Data

Appearance	Coloured Powder
Bulk Density	1.2 +/- 0.05
Pot Life	30 min @ 20°C
Curing Time	24 hours @ 20°C



www.rlapolymers.com.au

TECHNICAL ENQUIRIES TOLL FREE No.1800 752 679

Head Office:

215 Colchester Rd,
Kilsyth, VIC 3137
Ph: (03) 9728 1644
Fax: (03) 9728 6009

NSW:

363 Wentworth Ave,
Pendle Hill, NSW 2145
Ph: (02) 9636 7444
Fax: (02) 9636 7688

Queensland:

25 Computer Rd,
Yatala, QLD 4207
Ph: (07) 3807 4022
Fax: (07) 3807 4755

South Australia:

Blade Runner Distributors
2 Seaforth Ave,
Somerton Park, SA 5044
Ph: (08) 8358 5200
Fax: (08) 8358 5300

Western Australia:

Ph: 1800 242 931

New Zealand:

67 Dalgety Dr,
Manukau City
Auckland, NZ
Ph: 649 267 2772