

# Flexco Roofcoat Penetrating Sealer

## Roofcoat Penetrating Sealer

100% Acrylic Primer Sealer for concrete roof tiles

### PRODUCT FEATURES

100% Acrylic Polymer  
Excellent adhesion to concrete and masonry  
Good Alkali Resistance  
Excellent Re-coatability

<b>Colour</b>	White
<b>Appearance When Dry</b>	Clear
<b>Storage Temperature</b>	Minimum 10°C, Maximum 50°C
<b>Shelf Life</b>	18 months
<b>Pack Size</b>	20L

### ESTIMATION

<b>Solids Content (By Weight)</b>	40% + 1
<b>Dry film thickness</b>	50 microns @ 8 m <sup>2</sup> /L undiluted ; 25 microns @ 8 m <sup>2</sup> /L diluted 1:1
<b>Wet film thickness per coat</b>	110 microns per coat
<b>Theoretical Coverage</b>	6-8m <sup>2</sup> /L

### APPLICATION

#### Tile Preparation

“Roofcoat Penetrative Sealer” can only be applied once all repairs have been carried out, and that the roof has been thoroughly cleaned by water blasting after an initial moss and lichen treatment.

Ensure roof is free from all latence and contaminants.

Apply “Roofcoat Penetrative Sealer” liberally allowing product to soak into tile surface to saturation point. Avoid excessive runoff down roof and into guttering.

Pot life (@ 25 deg.C) – Single pack

Mixing – Stir thoroughly with a broad paddle to ensure product is fully incorporated.

### APPLICATION DETAILS

<b>Mixing Ratio</b>	1:1 - Sealer: Water
<b>Minimum Steel Temperature</b>	N/A
<b>Maximum Relative Humidity</b>	75%
<b>Application Temperature Range</b>	10°C - 35°C
<b>Methods</b>	Brush, Roller, Spray
<b>Thinners</b>	Water
<b>Cleaning Solvent</b>	Water
<b>Max. Volume Thinners</b>	5%
<b>Nozzle Orifice</b>	Airless Spray 15-20 Thou
<b>Fan Angle</b>	30° - 50°
<b>Nozzle Pressure</b>	2500 psi

# Flexco Roofcoat Penetrating Sealer

## DRYING CHARACTERISTICS

<b>Temperature (deg.C)</b>	10°	20°
<b>Touch dry</b>	2 hours	1 hour
<b>Handle dry</b>	4 hours	2 hours
<b>Full cure</b>	16 hours	8 hours

Overcoating – Where possible allow overnight dry between coats or as a minimum four hours at 20°c. Overcoat with “Roofcoat” coloured topcoat in either gloss, semi gloss or matt finish.

## SPECIAL PRECAUTIONS – HEALTH & SAFETY

Do not take internally. Avoid contact with eyes and prolonged contact with skin or breathing of spray mist. Use a dust/particulate respirator while spraying or sanding. Close containers after each use.

USE COMPLETELY OR DISPOSE OF PROPERLY. Hold unused paint in sealed container for special waste disposal. Do not discard into sewers or waterways.

USE ONLY WITH ADEQUATE VENTILATION.

KEEP OUT OF REACH OF CHILDREN.

## FIRST AID

**Eye Contact:** Flush immediately with plenty of running water. Get medical attention if irritation persists.

**Breathing Difficulty:** Leave area immediately to obtain fresh air. Get medical assistance if problem persists.

**If Swallowed:** Give water to dilute and get medical advice.

This information is intended to give a fair description of the product and its capabilities under specific test conditions. It does not constitute an offer by the manufacturers nor do they warrant or guarantee its accuracy of completeness in describing the performance or suitability of the product.

For further technical information please phone Flexco (NZ) Ltd - 09 2686970