

BITUPRIME

BITUMEN PRIMER FOR SELF-ADHESIVE MEMBRANES, AND OTHER BITUMINOUS PRODUCTS SUCH AS BITUMEN AND ASPHALT

Description	<p>Fast-drying, rubber modified bituminous priming solution, designed for sealing and preparation of surfaces for the application of roofing and waterproofing systems, in particular self-adhesive membranes. Also used in preparation of substrates requiring application of Bitumen or Asphalt.</p> <p>Drying time approximately 1 hour depending on the substrate and the weather conditions.</p>
Use	<ul style="list-style-type: none">• May be applied to many substrates including concrete, wood, brickwork, metal and old bitumen layers• For use with bitumen membranes, liquid maintenance products, bitumen and asphalt.
Application	<ul style="list-style-type: none">• Ideal application temperature should be between 10°C and 25°C.• Stir well before use, do not thin.• The substrate needs to be sound, clean and grease free.• Should algae or fungi be present, this must be removed with a stiff broom. Apply Bituprime Bitumen Primer in one coat with a brush, roller or airless spray gun. Only prime the area to be covered with membrane within 4 hours to prevent dust contamination. Porous surfaces may need two coats.• Make sure the primer is dry before applying bituminous membranes or liquid products.
Physical & chemical performances	<ul style="list-style-type: none">• Flash point: +/- 24°C• Relative density (water = 1): 0.90 and 0.95 g/cm³• Viscosity Fordcup 4 mm at 25°C: 65 — 75 sec• Dry extract: 55%
Coverage	<ul style="list-style-type: none">• Concrete 3-4 m²/ L• Bitumen 5 m²/L• Fibre Cement 10-12 m²/L• Metal 10-15 m²/L
Cleaning	WHITE SPIRITS
Packaging	20L STEEL PAILS
Storage	Containers should be kept sealed in a cool, dry, well-ventilated environment and all practical precautions taken against fire. Partly used containers may be re-sealed and used again after correct storage. To avoid the risk of spillage, always store and transport in a secure upright position.
Shelf Life	3 years in sealed packaging

Flexco (NZ) Ltd

67 Dalgety Drive, Manukau City. P: +64 9 268 6970, F: +64 9 268 6971, E: info@flexco-nz.co.nz
PO Box 98866 South Auckland Mail Centre, Manukau City, New Zealand



FLEXCO (N.Z.) LTD

SOLVING TOMORROWS BUILDING PROBLEMS - TODAY

BITUPRIME

Health & Safety

Keep container tightly sealed and away from direct heat. Keep away from sources of ignition. No smoking. Avoid contact with skin and eyes. Should there be contact with skin, wash immediately with soap and water or a recognized skin cleaner. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. In the event of accidents, seek medical attention immediately. Do not empty into drains. Do not allow solvent vapour to enter the air intakes of the ventilation systems of buildings.

Fire

In case of fire, use foam, dry powder, carbon dioxide or sand. Never use water jet.

Flexco (NZ) Ltd

67 Dalgety Drive, Manukau City. P: +64 9 268 6970, F: +64 9 268 6971, E: info@flexco-nz.co.nz
PO Box 98866 South Auckland Mail Centre, Manukau City, New Zealand



FLEXCO (N.Z.) LTD

SOLVING TOMORROWS BUILDING PROBLEMS - TODAY